


Reliable system – high yields. Bosch Solar Module a-Si plus

High-yield – easy-to-assemble – reliable.
Solar modules from Bosch Solar Energy.



BOSCH



NEW: positive power sorting starting July 1st 2010

Our thin-film modules offer impressive features including:

- ▶ Excellent annual yields for you and your customers, using non-toxic materials
- ▶ Higher specific yields due to positive power sorting
- ▶ Assembly systems that complement one another perfectly and are supplied from a single source thanks to collaborations with major assembly system manufacturers, including Bosch Rexroth
- ▶ Straightforward, solid installation with low assembly outlay through adaptability of recognized standard components
- ▶ Good usage options on e.g. east-facing, west-facing and slightly sloping roofs

Warranty conditions:

- ▶ 5 years product warranty
- ▶ 25-year performance guarantee (90% up to 12 years, 80% up to 25 years)
- ▶ Product certification to IEC 61646 and IEC 61730

Length [x]	Width [y]	Height [z]	Weight	Junction box	Plug connector	Cable [l]
1300	1100	7.1	25	MultiContact	MC4	plus 600 minus 1000
x, y, l in mm, -1 / +3 mm; z in mm, ±0.5 mm; weight in kg ±0.7						

Thin-film solar module	
Performance classes	75 Wp, 80 Wp, 85 Wp, 90 Wp
Performance sorting	±2.5 Wp (-0/+4.99 Wp NEW starting July 1 st 2010)
Structure	Frameless glass-glass laminate <ul style="list-style-type: none"> ▶ Thermally strengthened front glass ▶ PVB or EVA foil ▶ Thermally strengthened rear glass ▶ Junction box with bypass diode ▶ IP-Code Junction Box (IP 65)
Cells	Amorphous silicon Single-junction cell


Electrical characteristics for STC:**

Designation	Pmpp [Wp]	Vmpp [V]	Imp [A]	Voc [V]	Isc [A]	Voc initial [V]	Isc initial [A]
a-Si plus 90	90	99	0.90	141	1.13	143	1.19
a-Si plus 85	85	97	0.88	139	1.12	141	1.18
a-Si plus 80	80	95	0.85	137	1.11	139	1.17
a-Si plus 75	75	93	0.81	135	1.10	137	1.16
Reduction in module efficiency with decrease in irradiation level from 1000 W/m ² to 200 W/m ² (at 25 °C): -0.05% (absolute)							

Electrical characteristics for NOCT*:

Designation	Pmpp [W]	Vmpp [V]	Voc [V]	Isc [A]
a-Si plus 90	68	93	132	0.93
a-Si plus 85	65	91	130	0.92
a-Si plus 80	62	89	128	0.91
a-Si plus 75	57	87	126	0.90
NOCT: Normal Operation Cell Temperature 48.4 °C: Irradiation level 800 W/m ² , AM 1.5, temperature 20 °C, wind speed 1 m/s, electrical open circuit operation				

Dimensions*:



* Drawings and diagrams are not to scale. Detailed dimensions and tolerances are available on request.

** Electrical parameters are typical mean values from historical production data. Bosch Solar Thin Film GmbH assumes no liability for the accuracy of this data for future production batches. All data is subject to a measuring tolerance of ±3%.

Permissible operating and assembly conditions:

- ▶ Temperature range -40 °C to +85 °C, humidity max. 85% (rh)
- ▶ Upright assembly, laser lines running vertically
- ▶ Mechanical load-bearing capacity tested up to 2400 Pa
- ▶ Transformerless DC-AC converters are not permitted
- ▶ Maximum 1000 V system voltage

Weak light performance:

Intensity [W/m ²]	Vmpp [%]	Imp [%]
1000	0.0	0
800	-0.3	-15
600	-0.6	-36
400	-0.8	-58
200	-6.4	-79
The electrical data applies for 25 °C and AM 1.5.		

Thermal characteristics:

Temperature coefficient Pmpp	-0.21%/K
Temperature coefficient Voc	-0.28%/K
Temperature coefficient Isc	+0.04%/K
NOCT	42.2 °C

Bosch Solar Energy AG
 Wilhelm-Wolff-Str. 23
 99099 Erfurt
 Germany
 Phone: +49 361 2195-0
 Fax: +49 361 2195-1133
sales.se@de.bosch.com
www.bosch-solarenergy.de